



ArmorClear BTL™-9 AC

Clear Greenhouse Material w/ Anti Condensate

FABRICATION & WAREHOUSE	PRINEVILLE, OREGON	
WEIGHT	5.3 OZ./SQ.YD. (+/-10%)	
THICKNESS	9 MILS (+/-10%)	
COATING THICKNESS	2.25 MILS EACH (+/-10%)	
TENSILE STRENGTH (GRAB METHOD)	WARP 150 LBS. WEFT 130 LBS.	ASTM D 5034
TEAR STRENGTH (TONGUE METHOD)	WARP 50 LBS/INCH WEFT 50 LBS/INCH	ASTM D 5884
BURSTING STRENGTH (MULLEN)	250 PSI	ASTM D 3786
UV RESISTANCE	>80% STRENGTH RETAINED AFTER 2000 HRS.	ASTM G-151
LIGHT TRANSMITTANCE	NIR 78% Visible 87% Diffusion/Haze 63%	ASTM D 1003

ALL DATA IS DRAWN FROM U.S. TESTING AND PRECISION LABORATORIES.
2018