



ArmorCover BTL™-9 BW

FABRICATION & WAREHOUSE	PRINEVILLE, OREGON	
WEIGHT	4.4 OZ./SQ.YD. (+/-5%)	
THICKNESS	9 MIL (+/-10%)	ASTM D1777
COATING THICKNESS	1.75 MIL EACH (+/-5%)	
TENSILE STRENGTH (GRAB METHOD)	MD 150 LBS. TD 140 LBS.	ASTM D5024
TEAR STRENGTH (TONGUE METHOD)	MD 50 LBS/INCH TD 55 LBS/INCH	ASTM D2261-11
BURSTING STRENGTH (MULLEN)	270 PSI	ASTM D3786
LOW TEMPERATURE COLD CRACK	-40° F	ASTM D2136
UV RESISTANCE	>80% STRENGTH RETAINED AFTER 2000 HRS.	ASTM G-151

ALL DATA IS DRAWN FROM U.S. TESTING AND PRECISION LABORATORIES.
04/2018